


FORM PTO-1390 (REV 11-2000)	U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE	ATTORNEY'S DOCKET NUMBER 124-852
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371		U.S. APPLICATION NO. (If known, see 37.C.F.R. 1.5) 09/831,724 Unknown
INTERNATIONAL APPLICATION NO. PCT/GB99/04099	INTERNATIONAL FILING DATE 6 December 1999	PRIORITY DATE CLAIMED 8 December 1998
TITLE OF INVENTION ORGANIC LIGHT EMITTING MATERIAL AND DEVICE		
APPLICANT(S) FOR DO/EO/US WOOD et al.		
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:		
1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. 2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. 3. <input checked="" type="checkbox"/> This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below. 4. <input checked="" type="checkbox"/> The U.S. has been elected by the expiration of 19 months from the priority date (Article 31). 5. A copy of the International Application as filed (35 U.S.C. 371(c)(2)). a. <input type="checkbox"/> is attached hereto (required only if not communicated by the International Bureau). b. <input checked="" type="checkbox"/> has been communicated by the International Bureau. c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). 6. <input type="checkbox"/> An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)). a. <input type="checkbox"/> is attached hereto. b. <input type="checkbox"/> has been previously submitted under 35 U.S.C. 154(d)(4). 7. <input type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)). a. <input type="checkbox"/> are attached hereto (required only if not communicated by the International Bureau). b. <input type="checkbox"/> have been communicated by the International Bureau. c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)). 9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). 10. <input type="checkbox"/> A English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)). Items 11 To 20 below concern document(s) or information included: 11. <input type="checkbox"/> An Information Disclosure Statement under 37 C.F.R. 1.97 and 1.98. 12. <input checked="" type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 C.F.R. 3.28 and 3.31 is included. 13. <input checked="" type="checkbox"/> A FIRST preliminary amendment. 14. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. 15. <input type="checkbox"/> A substitute specification. 16. <input type="checkbox"/> A change of power of attorney and/or address letter. 17. <input type="checkbox"/> A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821-1.825. 18. <input type="checkbox"/> A second copy of the published international application under 35 U.S.C. 154(d)(4). 19. <input type="checkbox"/> A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4). 20. <input checked="" type="checkbox"/> Other items or information. PTO-1449/ International Search Report		

U.S. APPLICATION NO. (if known, see 37 C.F.R. 1.131) Unknown 31724		INTERNATIONAL APPLICATION NO. PCT/GB99/04099		ATTORNEY'S DOCKET NUMBER 124-852	
21. <input checked="" type="checkbox"/> The following fees are submitted:				CALCULATIONS PTO USE ONLY	
BASIC NATIONAL FEE (37 C.F.R. 1.492(a)(1)-(5): -- Neither international preliminary examination fee (37 C.F.R. 1.482) nor international search fee (37 C.F.R. 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO\$1000.00 -- International preliminary examination fee (37 C.F.R. 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO\$860.00 -- International preliminary examination fee (37 C.F.R. 1.482) not paid to USPTO but international search fee (37 C.F.R. 1.445(a)(2)) paid to USPTO\$710.00 -- International preliminary examination fee (37 C.F.R. 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4)\$690.00 -- International preliminary examination fee (37 C.F.R. 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4)\$100.00 ENTER APPROPRIATE BASIC FEE AMOUNT =				\$	860.00
				\$	0.00
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 C.F.R. 1.492(e)).				\$	0.00
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total Claims	11	-20 =	0	X	\$18.00
Independent Claims	1	-3 =	0	X	\$80.00
MULTIPLE DEPENDENT CLAIMS(S) (if applicable)					\$270.00
TOTAL OF ABOVE CALCULATIONS =				\$	860.00
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.				\$	0.00
SUBTOTAL =				\$	860.00
Processing fee of \$130.00, for furnishing the English Translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 C.F.R. 1.492(f)).				\$	0.00
TOTAL NATIONAL FEE =				\$	860.00
Fee for recording the enclosed assignment (37 C.F.R. 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 C.F.R. 3.28, 3.31). \$40.00 per property				\$	40.00
Fee for Petition to Revive Unintentionally Abandoned Application (\$1240.00 - Small Entity = \$620.00)				\$	0.00
TOTAL FEES ENCLOSED =				\$	900.00
				Amount to be:	
				refunded	\$
				Charged	\$
a. <input checked="" type="checkbox"/> A check in the amount of \$900.00 to cover the above fees is enclosed. b. <input type="checkbox"/> Please charge my Deposit Account No. 14-1140 in the amount of \$_____ to cover the above fees. A duplicate copy of this form is enclosed. c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 14-1140. A duplicate copy of this form is enclosed. d. <input checked="" type="checkbox"/> The entire content of the foreign application(s), referred to in this application is/are hereby incorporated by reference in this application.					
NOTE: Where an appropriate time limit under 37 C.F.R. 1.494 or 1.495 has not been met, a petition to revive (37 C.F.R. 1.137(a) or (b)) must be filed and granted to restore the application to pending status.					
SEND ALL CORRESPONDENCE TO: NIXON & VANDERHYE P.C. 1100 North Glebe Road, 8 th Floor Arlington, Virginia 22201-4714 Telephone: (703) 816-4000			 _____ SIGNATURE Arthur R. Crawford _____ NAME		
			25,327 REGISTRATION NUMBER		
			May 15, 2001 Date		

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of

WOOD et al.

Atty. Ref.: 124-852

Serial No. Unknown

Group:

Filed: May 15, 2001

Examiner:

For: ORGANIC LIGHT EMITTING MATERIAL AND DEVICE

* * * * *

May 15, 2001

Assistant Commissioner for Patents
Washington, DC 20231

Sir:

PRELIMINARY AMENDMENT

In order to place the above-identified application in better condition for examination,
please amend the application as follows:

IN THE CLAIMS

Please substitute the following amended claims for corresponding claims previously
presented. A copy of the amended claims showing current revisions is attached.

4. (Amended) A device according to claim 2 wherein the electrode closest to the substrate is the anode.

6. (Amended) A device according to claim 2 wherein the electrode furthest from the substrate is the cathode.

7. (Amended) A device according to claim 5 wherein the electrode modifying layer adjacent to the cathode comprises either MgF_2 or LiF .

WOOD et al.
Serial No. **Unknown**

9. (Amended) A device according to claim 1 wherein the organic layer further comprises a semi-conducting polymer.

10. (Amended) A device according to claim 1 wherein the organic layer further comprises one or more charge transporting compounds.

11. (Amended) A device according to claim 1 wherein the organic layer further comprises a substantially non-conducting polymer and charge transporting compounds.


REMARKS

The above amendments are made to place the claims in a more traditional format. Attached hereto is a marked-up version of the changes made to the claims by the current amendment. The attached page is captioned "**Version With Markings To Show Changes Made.**"

Respectfully submitted,

NIXON & VANDERHYE P.C.

By: _____



Arthur R. Crawford
Reg. No. 25,327

ARC:ms
1100 North Glebe Road, 8th Floor
Arlington, VA 22201-4714
Telephone: (703) 816-4000
Facsimile: (703) 816-4100

VERSION WITH MARKINGS TO SHOW CHANGES MADE

IN THE CLAIMS

4. (Amended) A device according to claim 2 [or 3] wherein the electrode closest to the substrate is the anode.
6. (Amended) A device according to claim 2 [or 3] wherein the electrode furthest from the substrate is the cathode.
7. (Amended) A device according to claim 5 [or 6] wherein the electrode modifying layer adjacent to the cathode comprises either MgF_2 or LiF .
9. (Amended) A device according to [any of the preceding claims] claim 1 wherein the organic layer further comprises a semi-conducting polymer.
10. (Amended) A device according to [any of the preceding claims] claim 1 wherein the organic layer further comprises one or more charge transporting compounds.
11. (Amended) A device according to [any of claims 1-8] claim 1 wherein the organic layer further comprises a substantially non-conducting polymer and charge transporting compounds.

ORGANIC LIGHT EMITTING MATERIAL AND DEVICE

This invention concerns new compositions and the use of such compositions in organic semi-conductor devices for example organic light emitting devices. In particular it relates to the use of luminescent boron fluoride complexes as a component of organic luminescent devices.

The use of organic electrically conducting materials as semiconductors in the fabrication of electronic devices has been explored by many investigators. Light emitting diodes have been demonstrated using a wide range of organic and molecular solids, including N,N'-diphenyl-N,N'-ditolylbenzidine, aluminium tris 8-hydroxyquinolate, 3-biphenyl-5-(4-t-butylphenyl)oxadiazole and poly(phenylene vinylene).

Conduction in organic semiconductors may be regarded as a two stage process. In the first stage, charge is injected into the organic material from the metal electrode. An example is injection of charge into evaporated thin films of 3-biphenyl-5-(4-t-butylphenyl)oxadiazole from a low work function electrode such as a magnesium metal electrode by application of a negative potential to the electrode. This injection of charge may also be regarded as an electrochemical reduction of the conducting material, or as electrochemical doping of the material. Other electronically conducting organic compounds may be subjected to charge injection by a positive potential, which is commonly applied via an electrode composed of a high work function metal such as gold. Such charge injection is commonly described as injection of positive charges denoted holes, and this description is understood to be equivalent to the extraction of electrons from the conducting material, which may also be regarded as an electrochemical doping or oxidation of the organic semiconductor.

In the second stage, charge is transported through the organic semiconductor layer. Conduction within electronically conducting organic solids involves, in practical materials, the transfer of electrical charge from one molecule to another. Such transfer of charge is described by a charge hopping or charge tunnelling mechanism which may allow an electron to overcome the energetic barrier between different molecules or molecular sub-units. In systems such as conjugated polymers including poly(acetylene) and poly(phenylenevinylene) charge can also flow along the conjugated chain by movement of charged discontinuities in the regular bonding sequence of the polymer. In such cases,

charge will normally be transferred through the bulk sample by a large number of individual molecules, and hopping or tunnelling remains an important mechanism.

In order to achieve efficient light emission from an organic electroluminescent device, it is desirable for respectively positively charged and negatively charged carriers to become simultaneously localised on a single molecule or on a small number of molecules in mutual close proximity. Such localisation of oppositely charged carriers leads to production of a molecule in its excited state, or to an excimer or exciplex comprising a plurality of molecules in an electronically excited state. Such electronically excited species, especially in the case of conjugated polymers, may also be termed exciton states.

Localisation of respectively positive and negative charge carriers may be achieved in several ways. By virtue of their opposite electronic charges, a coulombic attraction exists between them which tends to lead to localisation. Under the high electric field gradients typical of an operating device, such localisation may be ineffective in achieving high operating efficiency from devices. A known route to achieving high efficiency in devices is to use two organic semiconductor layers, one of which transports only positive carriers (holes) and the other transports only negative carriers (electrons). Under operating conditions, a high density of carriers of each sign is deposited at the interface or junction formed by the two layers, increasing the probability of their combination to form an electronically excited state. Such devices can show high efficiency but suffer the disadvantage that they require fabrication of a multilayer organic structure. Single layer structures may admit the passage of both electron and holes. Improved efficiency of operation in such single layer devices can be obtained by including in the composition a luminescent material (i.e. a dopant) at low concentration, preferably selected as having both an electron affinity higher than that of the principal negative charge carrying species in the semiconductor, and an ionisation potential lower than that of the principal positive charge carrying species in the layer. Under this condition, the luminescent material traps injected charge carriers of each polarity, increasing the probability of their combination.

The electronically excited states obtained by combination of charge carriers may be obtained in conditions of different total electronic spin, especially in so-called singlet states and triplet states respectively. It is understood that in order to obtain high luminescence efficiency, the singlet states of excited species are most effective in many cases due to the possibility of their radiative decay to an electronic ground state with emission of a

It is known that other routes exist by which the energy may be lost from an excited state, without emission of a photon of light. Non-radiative decay results in conversion of the energy to heat within the material. In most organic materials, non-radiative decay is the usual route to loss of energy from excited triplet states, as well as being a competitive process to the desirable fluorescence. A further route to loss of energy from an excited singlet state is its transition to a triplet state, followed by non-radiative decay. It is desirable in many practical devices that both direct non-radiative decay routes and the transformation of singlet states to triplet states should be minimised to achieve the highest efficiency in the device.

Some of the compounds described by the current invention are known to show high luminescence efficiency and stability, and to provide a low probability of crossing from an excited singlet state to a triplet state. In addition some of the compounds of formula I have been proposed, for example as laser dyes, and a number of compounds described by the present invention are offered commercially for this purpose.

Dodabalapur in Solid State Communications, vol 102, No2-3, pp259-267, 1997 describes the use of a pyromethene in combination with Alq3 wherein the commercially available pyromethene PM580 is present as a dopant (which may also be referred to as a light emitter) and the Alq3 is an electron transporter. In this case, no particular benefit is revealed from the use of PM580 against the known incorporation of luminescent materials such as rubrene, coumarin 6 and quinacridone derivatives into Alq3 layers in such devices. Such a route to device fabrication necessitates the use of a co-evaporation of Alq3 and dopant which requires complex facilities for its success and/or is difficult to control in practise.

Japanese patent Kokai number 9-289081 describe the use of BF₂ – containing compounds in organic electroluminescent devices. Those devices comprise an anode, a hole transport layer, an organic electron transport layer and a cathode stacked in succession where the hole transport layer and/or organic electron transport layer contain(s) a pyrromethane-BF₂ complex. In addressing the problems of the prior art, the invention disclosed in JP 9-289081 aims to provide devices whose light emission spectra


have a small half maximum full-width – i.e. a narrow emission spectrum thus leading to some control of the colour produced.

Up until now it has proved difficult to provide single layer OLED devices without compromising the overall performance – in particular the brightness and efficiency.

It has unexpectedly been found that compounds of the present invention show advantageous properties in respect of their ability to act as radiative combination sites for charges in organic electroluminescent structures and as electron transporting layers in OLEDs.


09034724.051504
"4242E850"

According to this invention an organic light emitting diode device comprises a substrate bearing an organic layer sandwiched between electrode structures wherein the organic layer comprises a hole transporter, an electron transporter and a light emitter wherein the electron transporter or the light emitter or the electron transporter and the light emitter comprise a material of general formula I:




Formula I


wherein $\overset{\text{A}}{\text{---}} \overset{\text{D}}{\text{---}}$ is selected from the following:



wherein A and D are both N, and the ring systems are, independently of each other, optionally substituted with one or two or three groups independently selected from C1 - C8 straight chain or branched chain alkyl or alkoxy; Q is CN or H or C₁₋₈ straight chain or branched chain alkyl;



wherein A and D are given by O or N, X is given by C₁₋₅ straight chain or branched chain alkyl or alkoxy and the ring systems are, independently of each other, optionally substituted with one or more groups J and L independently selected from C1 - C8 straight chain or branched chain alkyl or alkoxy wherein j is selected from 0-4 and l is selected from 0-2;




wherein A and D are given by O or N and the ring systems are, independently of each other, optionally substituted with one or more groups

U, V, W independently selected from C1 - C8 straight chain or branched chain alkyl or alkoxy wherein u is 0-4, v is 0-2 and w is 0-2;

characterised in that the organic layer is a single layer.

By stating that the organic layer is a single layer it is meant that the electron transport, hole transport and light emitting functions are provided by a single layer.

Optionally there may be a layer (i.e. an electrode modifying layer) between one of the electrodes and the organic layer. This layer is preferably an organic material and comprises examples of known materials such as copper phthalocyanine (CuPc), polyaniline, PEDOT wherein PEDOT is the following:



doped with polystyrene sulphonic acid.

Preferably the organic electrode modifying layer is the layer closest to the substrate – in turn the electrode which it is adjacent to is preferably the anode. The function of the electrode modifying layer includes assistance of hole injection and planarisation of the anode. A further function of the electrode modifying layer may include inhibition of diffusion of material, eg., oxygen or indium, from the electrode into the organic layer.

Optionally, in addition or alternatively, there may be present a layer of an electrode modifying layer between the organic layer and the other electrode which is usually furthest from the substrate – i.e. usually the cathode; this is preferably an inorganic layer and examples include LiF and MgF₂. This layer assists in electron injection.

In general the electrode modifying layers may be conducting or insulating.

Preferably the electrode furthest from the substrate is the cathode and preferably it comprises Al or an Al alloy or Mg or MgAg.

Preferably the electrode closest to the substrate is the anode.

Preferably the organic layer further comprises a semiconducting polymer e.g. polyvinylcarbazole. In addition or instead of the semiconducting polymer there may be one or more dispersed charge transporting compounds present.

Alternatively, rather than a semiconducting polymer being present there may be an electronically inert polymer present (i.e. one that is substantially non-conducting) in which case there is also present one or more charge transporting compounds.

According to a further aspect of this invention a composition suitable for use as an organic layer in an OLED device comprises a material of general formula I.

TOP SECRET

Compounds of Formula I show advantageous combinations of properties when used in organic light emitting devices.

The structural and other preferences are expressed below on the basis of desirable characteristics, in particular an advantageous combination of electronic orbital energy levels which is one factor determining the effectiveness of capture and recombination of electronic charge carriers in a light emitting device, luminescence quantum efficiency, solubility, processability and high chemical and photochemical stability of the material in storage and in operating devices. The present invention may give rise to devices which exhibit, inter alia, one or more of the following advantages - higher brightness, higher efficiency, purer spectral colours, longer operating life, lower cost of manufacture.

Preferably the compounds of formula I are present as:

1. light emitters
2. electron transporters and light emitters.

Preferred materials of Formula 1 include boron fluoride adducts of pyrromethenes and of diketones, di-imines and ketoimines.

Advantages associated with single layer devices are the ease of fabrication and lower costs. Also single layer devices allow for solution processing without the necessity of using materials with orthogonal solvent properties.

Overall preferred structures for formula I are those listed below :

1,2,3,5,6,7-hexamethyl-8-cyanopyrromethene-difluoroborate complex

1,3,5,7,8-pentamethyl-2,6-di-t-butylpyrromethene-difluoroborate

1,3,5,7,8-pentamethyl-2,6-di-n-butylpyrromethene-difluoroborate

1,3,5,7,8-pentamethyl-2,6-diethylpyrromethene-difluoroborate

1,3,5,7,8-pentamethylpyrromethene-difluoroborate

1-(1-(difluoroboryl)oxy-3,4-dihydro-naphthalen-2-yl)-ethanone

1-(1-(difluoroboryl)oxy-3,4-dihydro-6-methoxy-naphthalen-2-yl)-ethanone

1-(1-(difluoroboryl)oxy-3H-benzo(f)chromen-2-yl)-ethanone

Compounds of Formula I may be prepared by known routes, including those described in US patents 4,916,711 and 5,189,029. Typically said preparative routes comprise reaction of boron trifluoride with a diketone, diimide or ketoimide. Routes to these compounds are well known in the art.

0983724-051504
T098750-427E960

The invention will now be described with reference to the following diagrams by way of example only:

Figure 1 illustrates an Organic Light Emitting Diode (OLED) device incorporating the materials of the present invention.

Figure 2 illustrates a matrix addressed OLED in plan view.

Figure 3 illustrates the variation of current passed as a function of applied voltage by a device given by Figure 1 - see Example 1.

Figure 4 illustrates the spectrum of emitted light corresponding to Example 1.

Figure 5 illustrates the variation of current passed as a function of applied voltage by a device given by Figure 1 - see Example 2.

Unless otherwise stated all reagents used are commercially available from the Aldrich Chemical Company.

0374 0540
T0374 0540

The following compounds are illustrative examples which have been synthesised according to the present invention:

Example 1

A solution was prepared containing 0.2g N,N'-diphenyl-N,N'-di-3-tolylbenzidine purchased from Syntec GmbH of Industriepark Wolfen-Thalheim, Werkstattstrasse 188, 06766-Wolfen, Germany, 0.2g 2-(4-t-butylphenyl)-5-biphenyl-1,3,4-oxadiazole, 0.2g poly-N-vinylcarbazole and 0.00016g of 1,3,5,7,8-pentamethyl-2,6-di-n-butylpyrromethene-difluoroborate in 6.5g of 1,2-dichlorobenzene. 1,3,5,7,8-pentamethyl-2,6-di-n-butylpyrromethene-difluoroborate was purchased as laser dye PM580 from AG Electro-Optics, Farside House, Tarporley Business Centre, Tarporley, Cheshire. A 2 inch square piece of ITO coated glass (Balzers, 100Ω/sq) was cleaned by rinsing in acetone and isopropanol, then spin coated with the above solution at 1000rpm for 30 seconds. The coated glass was immediately transferred to a heated plate at 90°C and dried for 5 minutes, then heated at 90°C in an oven for 30 minutes. The plate was transferred to a vacuum coating apparatus and aluminium was deposited onto the polymer through a perforated metal mask to form a pattern of circular aluminium contacts 3.5mm across with a thickness of 1000Å at a rate of 4 Å/second at a pressure of 10⁻⁶ torr. After coating, the device was removed from the coating equipment and electrical contact made to the ITO glass by means of a wire attached by indium solder.

A gold wire was used to make electrical contact to each of the aluminium contact pads, and a negative potential applied. Light emission could be easily observed from the ITO glass side of the device.

A Keithley 236 source measure unit was used to measure the variation of current passed by a sample device as a function of applied voltage. The results are shown in Figure 3.

The spectrum of the emitted light was measured by means of a Photo Research type 714 spot photometer, and is shown in Figure 4.

Example 2

A device was prepared in the same manner and using identical conditions to those employed in Example 1, save that the metal contacts were formed from thermally evaporated samarium instead of aluminium. The variation of current passed by a sample device as a function of applied voltage is presented in Figure 5. The emission spectrum was essentially identical to that shown in Figure 4 for the device of Example 1.

Example 3

A solution was prepared containing 0.2g 2-(4-t-butylphenyl)-5-biphenyl-1,3,4-oxadiazole, 0.4g poly-N-vinylcarbazole and 0.00018g of 1,2,3,5,6,7-hexamethyl-8-cyanopyrromethene-difluoroborate complex in 6.5g of 1,2-dichlorobenzene. 1,2,3,5,6,7-hexamethyl-8-cyanopyrromethene-difluoroborate complex was purchased as laser dye PM650 from AG Electro-Optics, Farside House, Tarporley Business Centre, Tarporley, Cheshire. The solution was used in the fabrication of a light emitting device in the same manner as Example 2.

On application of a negative potential of 40V to the samarium contacts, emission of deep red light was visible.

PCT/GB99/04099

An Organic Light Emitting Diode (OLED), which is a type of semiconductor device, suitable for incorporating materials of the present invention is illustrated in Figure 1. The device comprises two electrodes 1a, 1b, at least one of the electrodes is transparent to light of the emission wavelength of a layer of organic material 3. The other electrode may be a metal, for example Mg, Li, Ca, Al or an alloy of metals, for example MgAg, LiAl or a double metal layer, for example Li and Al or Indium Tin Oxide (ITO). One or both electrodes 1a, 1b may consist of organic conducting layers. A processing surface or substrate 2 may be made of any material which is flat enough to allow subsequent processing, for example glass, silicon, plastic. The substrate 2 may be transparent to the emitted radiation of the organic material 3. Alternatively one of the electrodes 1a, 1b may be transparent instead. If electrode 1a is transparent then preferably the substrate is transparent too. Sandwiched between the electrodes 1a and 1b is a layer of organic material 3 which consists of one layer. The layer of organic material 3 possesses the following three properties: electron transporting (ET); hole transporting (HT); light emitting (LE). The materials described by the current invention are suitable for use as electron transporters and/or light emitters. The organic material may consist of a single material, or of two or more materials with appropriate properties mixed together. Suitable hole and/or electron transport materials include conjugated polymers such as polyphenylenevinylene (PPV) or MEHPPV, amine derivatives such as triphenylamine or TPD, heterocyclic compounds such as diphenyloxadiazole and triphenyltriazole, and heterocyclic polymers such as poly(pyridine).

The LE material may act as a dopant in small quantities - typically 0.5% into ET or HT or both.

Preferably the luminescent material has a high quantum efficiency of luminescence.

The layer of organic material 3 may be deposited on the electrode 1a by any of the following techniques: thermal evaporation under vacuum, sputtering, chemical vapour deposition, spin depositing from solution or other conventional thin film technology. The thickness of the layer of organic material 3 is typically 10-1000nm, preferably 20-200nm.

The device may contain layers 4a and 4b (electrode modifying layers) which are situated next to the electrodes 1a and 1b, these layers 4a and 4b may be conducting or insulating and act as a barrier to diffusion of the electrode material or as a barrier to chemical reaction at the electrode 1a, 1b and layer of organic material 3 interface. Examples of suitable materials for 4a and 4b include emeraldine which prevents indium diffusion into the layer of organic material 3 from an ITO electrode, or, for the same reason, copper phthalocyanine may be used; alternatively the addition of a thin layer (~0.5nm) of lithium or magnesium fluoride at the interface between a metal electrode and the layer of organic material 3 may be used.


The device of Figure 1 may be a single pixel device or it may be matrix addressed. An example of a matrix addressed OLED is shown in plan view in Figure 2. The display of Figure 2 has the internal structure described in Figure 1 but the substrate electrode 5 is split into strip-like rows 5l to 5m and similar column electrodes 6l to 6n, this forms an m x n matrix of addressable elements or pixels. Each pixel is formed by the intersection of a row and column electrode.

A row driver 7 supplies voltage to each row electrode 5. Similarly, a column driver 8 supplies voltage to each column electrode. Control of applied voltages is from a control logic 9 which receives power from a voltage source 10 and timing from a clock 11.

Alternatively the device may be a multi-pixel device with each pixel addressed independently by a separate electrical connection or by an active matrix backplane.


Claims

1. An organic light emitting diode device comprising a substrate bearing an organic layer sandwiched between electrode structures wherein the organic layer comprises a hole transporter, an electron transporter and a light emitter wherein the electron transporter or the light emitter or the electron transporter and the light emitter comprise a material of general formula I




Formula I


wherein $\overset{\text{A}}{\text{---}} \overset{\text{D}}{\text{---}}$ is selected from the following:



wherein A and D are both N, and the ring systems are, independently of each other, optionally substituted with one or two or three groups independently selected from C1 - C8 straight chain or branched chain alkyl or alkoxy; Q is CN or H or C₁₋₈ straight chain or branched chain alkyl;



wherein A and D are given by O or N, X is given by C₁₋₅ straight chain or branched chain alkyl or alkoxy and the ring systems are, independently of each other, optionally substituted with one or more groups J and L independently selected from C1 - C8 straight chain or branched chain alkyl or alkoxy wherein j is selected from 0-4 and l is selected from 0-2;



wherein A and D are given by O or N and the ring systems are, independently of each other, optionally substituted with one or more groups U, V, W independently selected from C1 - C8 straight chain or branched chain alkyl or alkoxy wherein u is 0-4, v is 0-2 and w is 0-2;

characterised in that the organic layer is a single layer.

2. A device according to claim 1 wherein at least one of the electrodes has an electrode modifying layer at the electrode/organic layer interface.
3. A device according to claim 2 wherein there are electrode modifying layers at both electrode/organic layer interfaces.
4. A device according to claim 2 or 3 wherein the electrode closest to the substrate is the anode.
5. A device according to claim 4 wherein the electrode modifying layer adjacent to the anode comprises either PEDOT or polyaniline.
6. A device according to claim 2 or 3 wherein the electrode furthest from the substrate is the cathode.
7. A device according to claim 5 or 6 wherein the electrode modifying layer adjacent to the cathode comprises either MgF_2 or LiF .
8. A device according to claim 7 wherein the cathode is made from Al, Al alloy, Mg or MgAg.
9. A device according to any of the preceding claims wherein the organic layer further comprises a semi-conducting polymer.

10. A device according to any of the preceding claims wherein the organic layer further comprises one or more charge transporting compounds.
11. A device according to any of claims 1-8 wherein the organic layer further comprises a substantially non-conducting polymer and charge transporting compounds.

0904742660

1/3

Fig.1.





Fig.2.



2/3

Fig.3.






Fig.4.



3/3

Fig.5.



RULE 63 (37 C.F.R. 1.63)
DECLARATION AND POWER OF ATTORNEY
FOR PATENT APPLICATION
IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

As a below named inventor, I hereby declare that my residence, post office address and citizenship are as stated below next to my name, and I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

ORGANIC LIGHT EMITTING MATERIAL AND DEVICE

the specification of which (check applicable box(es)):

☐ is attached hereto

☐ was filed on

☒ was filed as PCT International application No.

as U.S. Application Serial No.

PCT/GB99/04099

on Atty Dkt. No. P2746/USW

06 December 1999 (06/12/1999)

and (if applicable to U.S. or PCT application) was amended on

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above. I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with 37 C.F.R. 1.56. I hereby claim foreign priority benefits under 35 U.S.C. 119/365 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed or, if no priority is claimed, before the filing date of this application:

Priority Foreign Application(s):

Application Number
9826845.1

Country
GB

Day/Month/Year Filed
08 December 1998

I hereby claim the benefit under 35 U.S.C. §119(e) of any United States provisional application(s) listed below.

Application Number

Date/Month/Year Filed

I hereby claim the benefit under 35 U.S.C. 120/365 of all prior United States and PCT international applications listed above or below and, insofar as the subject matter of each of the claims of this application is not disclosed in such prior applications in the manner provided by the first paragraph of 35 U.S.C. 112, I acknowledge the duty to disclose material information as defined in 37 C.F.R. 1.56 which occurred between the filing date of the prior applications and the national or PCT international filing date of this application:

Prior U.S./PCT Application(s):

Application Serial No.

Day/Month/Year Filed

Status: patented
pending, abandoned

PCT/GB99/04099

06 December 1999

PENDING

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon. And I hereby appoint NIXON & VANDERHYE P.C., 1100 North Glebe Rd., 8th Floor, Arlington, VA 22201-4714, telephone number (703) 816-4000 (to whom all communications are to be directed), and the following attorneys thereof (of the same address) individually and collectively my attorneys to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith and with the resulting patent: Arthur R. Crawford, 25327; Larry S. Nixon, 25640; Robert A. Vanderhye, 27076; James T. Hosmer, 30184; Robert W. Faris, 31352; Richard G. Besh, 22770; Mark E. Nusbaum, 32348; Michael J. Keenan, 32106; Bryan H. Davidson, 30251; Stanley C. Spooner, 27393; Leonard C. Mitchard, 29009; Duane M. Byers, 33363; Jeffry H. Nelson, 30481; John R. Lastova, 33149; H. Warren Burnam, Jr. 29366; Thomas E. Byrne, 32205; Mary J. Wilson, 32955; J. Scott Davidson, 33489; Alan M. Kagen, 36178; William J. Griffin, 31260; Robert A. Molan, 29834; B. J. Sadoff, 36663; James D. Berquist, 34776; Updeep S. Gill, 37334; Michael J. Shea, 34725; Donald L. Jackson, 41090; Michelle N. Lester, 32331.*

1. ∞ Inventor's Signature:  Date: 3/5/01

Inventor:

Emma
(first)

L
MI

Wood
(last)

GB
(citizenship)

Residence: (city)

Malvern GB

(state/country) Worcs, GB

Post Office Address:
(Zip Code)

DERA Malvern, St Andrews Road, Malvern, Worcs
WR14 3PS

2. ∞ Inventor's Signature:  Date: 4/5/01

Inventor:

Ian
(first)

C
MI

Sage
(last)

GB
(citizenship)

Residence: (city)

Malvern GB

(state/country) Worcs, GB

Post Office Address:
(Zip Code)

DERA Malvern, St Andrews Road, Malvern, Worcs
WR14 3PS

FOR ADDITIONAL INVENTORS, check box ☐ and attach sheet with same information and signature and date for each.